



中国建材

www.zfsycf.com.cn

ZHONGFU SHENYING CARBON FIBER

Product & Packaging chart



www.zfeurope.eu

revised date: February 2023

MODEL	TOW	Tensile strength	Elastic Modulus	Elongation at Break	Linear density/tex	Density g/cm ³	Filament diam.	Bobbin weight /kg	Bobbins /box	Box weight /kg	Boxes /pallet	Pallet weight /kg
SYT45	3K	4000	230	1,7	198	1,79	7	1	15	15	36	540
SYT45S	12K	4500	230	1,9	800	1,79	7	4	6	24	36	864
	24K	4500	230	1,9	1600	1,79	7	6	6	36	30	1080
SYT49S	12K	4900	230	2,1	800	1,79	7	4	6	24	36	864
	24K	4900	230	2,1	1600	1,79	7	6	6	36	30	1080
SYT55G	12K	5900	295	2	450	1,79	5	2	12	24	36	864
SYT55S	12K	5900	295	1,9	450	1,79	5	1/2	15/12	15/24	36	540/864
	24K	5900	295	1,9	900	1,79	5	2	12	24	36	864
SYT65	12K	6400	295	2,1	450	1,79	5	2	12	24	36	864

ZHONGFU-SHENYING CARBON FIBRE Co. Ltd EUROPEAN REPRESENTATIVE

NADALIA CONSULTING di Nadia Bosis

nadiabosis@nadalialia.it www.nadalialia.it

mobile +39 3286577284