



中国建材

[www.zfsycf.com.cn](http://www.zfsycf.com.cn)

## ZHONGFU SHENYING CARBON FIBER

Product & Packaging chart



[www.zfeurope.eu](http://www.zfeurope.eu)

revision date: June 2023

MODEL*	TOW	Tensile strength	Elastic Modulus	Elongation at Break	Linear density/tex	Density g/cm <sup>3</sup>	Filament diam.	Bobbin weight /kg	Bobbins /box	Box weight /kg	Boxes /pallet	Pallet weight /kg
SYT45	3K	4000	230	1,7	198	1,79	7	1	15	15	36	540
SYT45S	12K	4500	230	1,9	800	1,79	7	4	6	24	36	864
	24K	4500	230	1,9	1600	1,79	7	6	6	36	30	1080
	48K**	4500	235	1,9	3200	1,8		8	3	24		
SYT49S	12K	4900	230	2,1	800	1,79	7	4	6	24	36	864
	24K	4900	230	2,1	1600	1,79	7	6	6	36	30	1080
	24KGEN2**	5500	255	2,1	1600	1,79		6	6	36	30	1080
SYT55S	12K	5900	295	1,9	450	1,79	5	1/2	15/12	15/24	36	540/864
	24K**	5900	295	2								
SYM40	12K	4500	377	1,1	430	1,78	7	0,62	15	9,3	36	334,8

\*selected products with availability for European market

\*\* new

ZHONGFU-SHENYING CARBON FIBRE Co. Ltd EUROPEAN AGENT

NADALIA CONSULTING di Nadia Bosis

[nadiabosis@nadalia.it](mailto:nadiabosis@nadalia.it) [www.nadalia.it](http://www.nadalia.it)

mobile +39 3286577284